

Sub-
G1
Cont

(b) laterally blowing ammonia gas against the falling droplets so that the surfaces of the falling droplets are substantially evenly gelled in a substantially spherical shape,

wherein the ammonia gas is blown from at least one nozzle disposed on a ring interior and, if necessary, at least one nozzle disposed on a ring exterior;

(c) allowing the falling droplets to drop into an aqueous ammonia solution and coagulate to form substantially spherical aluminum beads;

E1

(d) collecting the aluminum beads from the aqueous ammonia solution.

a

20. The process according to claim 19 which further comprises the step of drying the aluminum^{oxide} beads.

a

21. The process according to claim 20, wherein the aluminum^{oxide} beads are dried at a temperature of 20 - 300°C for 1 to 24 hours.

a

22. The process according to claim 19 which further comprises the step of calcining the aluminum^{oxide} beads.

a

23. The process according to claim 22 wherein the aluminum^{oxide} beads are calcined for 2-12 hours at 500 to 700°C.